

Composition Composición	100% Acrylic 100% Acrílico
Weight Peso	220 g/m ² 6.5 oz/yd ²
Width Ancho	160 cm 63"
Rapport	5,3 cm 2.1"
Lenght of Roll Longitud de las piezas	50 ml 54.7 yd
Finish Acabado	Water Repellent Hidrofugado
Colour Fastness to Light Solidez del color a la luz	6 / 7 ISO 105 B 02 2014-11 method 2
Colour Fastness to Rubbing Solidez del color al frote	4-5/5 UNE EN ISO 105-X12:2016
Colour Fastness to Chlorinated Water Solidez del color al agua clorada	5/5 UNE EN ISO 105-E03:2010
Ultraviolet Protection Factor UPF Factor de protección ultravioleta UPF	50+ AZ/NZS 4399/1996
Spray Test	5/5 UNE EN ISO 24920
Water Repellency Repelencia al agua	6 / 6 AATCC-193
Oil Repellency Repelencia al aceite	5 / 6 AATCC-118
Tear Resistance Resistencia al desgarro	986 Warp / Urdimbre 525 Weft / Trama UNE EN ISO 13936-1:1999
Slippage Resistance Deslizamiento a la costura	467.64 Warp / Urdimbre 183.44 Weft / Trama UNE EN ISO 13936-1:2004
Resistance to Pilling Resistencia al pilling	4-5 / 5 UNE EN ISO 12945-2:2001
Abrasion Resistance (Martindale) Resistencia a la abrasión (Martindale)	20000 UNE EN ISO 12497-2:2016
Shrinkage to Washing/Drying Encogimiento al lavado/secado	-0.20 % Warp / Urdimbre 0.00% Weft / Trama UNE EN ISO 5077:2008
Cleaning Instructions Manutención	    

Uses Usos



Qualities Cualidades



WATER REPELLENT
HIDROFUGO



STAIN RESISTANT
ANTIMANCHAS



MOULD RESISTANT
ANTIMOHO



UV PROTECT
PROTECCIÓN UV



UV RESISTANT
RESISTENCIA UV



DURABLE
DURADERO



EASY TO CLEAN
FÁCIL DE LIMPIAR

Sensitive values of tolerance of +/- 5%. Valores susceptibles de tolerancia de +/- 5%.

The Acrisol warranty covers an abnormal deterioration of the fibre due to the loss of colour or resistance whenever there are normal exposure conditions, including sun, mould, rot and atmospheric agents in general, and as long as the fibre has been installed, used and maintained correctly. The guarantee does not cover the installation work of the distributor, it only replaces the affected tissue footage. The warranty also does not cover, in any case, the deterioration due to abusive use, accidental burns, negligence or perforation.

La garantía Acrisol cubre un anormal deterioro de la fibra debido a la pérdida de color o resistencia siempre que existan unas condiciones de exposición normales, incluyendo el sol, moho, putrefacción y agentes atmosféricos en general, y siempre y cuando la fibra haya sido instalada, utilizada y mantenida correctamente. La garantía no cubre los trabajos de instalación del distribuidor, sólo repone el metraje de tejido afectado. La garantía tampoco cubre, en cualquier caso, el deterioro debido al uso abusivo, quemaduras accidentales, negligencia o perforación.